

COOLGUARD® HRL36

WATER
 CONTAINMENT

CoolGuard® HRL36 | 36 mils

Base Fabric	Standard	Metric
Base Fabric Weight	8 oz / yd ²	270 g / m ²
Fiber / Style	Polyester / Leno	

Coated Fabric	Standard	Metric
Total Weight (nominal)	30 oz / yd ²	1,015 g / m ²
Thickness (+/- 10%)	36 mils	0.91 mm
Coating Type	Ethylene Terpolymer PVC Alloy	
Coating Distribution	50 / 50	
Sealing Properties	Dielectric, Thermal	

Material Properties	ASTM Test Methods	Standard	Metric
Tensile Strength, Grab (Warp / Fill)	D751A	625 / 600 lbs	2,780 / 2,670 N
Tear Strength, Tongue (Warp / Fill)	D751B (mod)	120 / 120 lbs	534 / 534 N
Puncture, Flat Tip	D4833	220 lbs	979 N
Puncture, Ball	D751	1,000 lbs	4,450 N
Puncture, Pyramid	FTMS 101C, 2031	375 lbs	1,670 N
Hydrostatic Resistance	D751A	800 psi	5.52 MPa
Dimensional Stability (212°F 100°C / 1h)	D1204	2.5% max.	
Ply Adhesion	D751 (mod)	25 lbs / 2 in	111 N / 5 cm
Thermal / R.F. Adhesion	D751	20 lbs / in	35 N / cm
Low Temp Bend (1" Mandrel)	D2136	-40°F max.	-40°C max.
UV Resistance	G23	8,000 hrs	

A variety of standard widths and colors are available.

A One-Stop Shop. Cooley is the leading provider of a complete range of commercial and potable water-grade geomembranes—including Coolpro® reinforced polypropylene, Coolthane® polyurethane coated fabrics, and Coolshield® for high-temperature and extreme containment applications—to provide cost-competitive solutions for a wide, highly diverse range of applications.



The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

For further information, please contact Engineered Membranes: 401.724.9000 or eminfo@cooleygroup.com