Tensar RE580 Geogrid Model Specification In Soil Temperature 20°C

- 1. The reinforcing element shall be a geogrid manufactured in accordance with a Quality Management System which complies with the requirements of BS EN ISO 9001:2000. If required by the Engineer, the Contractor shall provide evidence that the manufacturer's Quality Assurance System has been certified to conform with BS EN ISO 9001:2000 by an external authenticating authority approved by the Department of Trade and Industry.
- 2. The reinforcing element shall be a geogrid manufactured from high density polyethylene sheet, oriented in one direction so that the resulting ribs shall have a high degree of molecular orientation which is continued through the integral transverse bar.
- 3. The long term creep rupture strength P_C (Ultimate Limit State), for a design life of 120 years, shall be 65.27kN/m and 64.48kN/m for 60 years at a mean temperature of 20°C. This shall be determined by application of standard extrapolation techniques to creep data obtained in accordance with BS EN ISO 13431:1999 and shall be a lower bound value. Values shall be based on a geogrid family lineage of a minimum 100,000 hour of continuous creep testing.
- 4. The geogrid shall have an appropriate partial factor for site installation and construction damage, determined by the particle size distribution of the reinforced fill and in accordance with the values used in the design. This factor shall be based on full scale tests carried out in accordance with BS 8006:1995 Annex D on fill types similar in grading to those used in the design and witnessed by an independent approval authority. If required by the Engineer, the Contractor shall provide supporting documented evidence of testing for this and any other partial factors assumed in the design. Partial factors for site installation and construction damage based on limited laboratory based testing are not acceptable.
- The strength of the junctions between the longitudinal ribs and transverse bars, as determined by the Geosynthetics Research
 Institute, Drexel University, USA, Test Method GG2-87, and expressed as a percentage of Quality Control Strength shall be not
 less than 95%.
- 6. The reinforcing element shall be the subject of a current and relevant Roads and Bridges Agrément Certificate issued by the British Board of Agrément for walls and bridge abutments.
- 7. The minimum geogrid roll width shall be 1.3m.
- 8. Any site joints in the reinforcement roll length shall be capable of carrying in the full long term creep rupture strength when tested in soil and have evidence of testing from a reputable independent test body. If required by the Engineer the Contractor shall provide evidence of this, or carry out testing to demonstrate geogrid to geogrid joint performance.
- 9. The geogrid shall be inert to all chemicals naturally found in soils and shall have no solvents at ambient temperature. It shall not be susceptible to hydrolysis, shall be resistant to aqueous solutions of salts, acids and alkalis (pH = 2.0 to 12.5), shall be non-biodegradable and shall have a minimum of 2% finely divided carbon black, as determined by BS 2782:Part 4:Method 452B:1993, well dispersed in the polymer matrix to inhibit attack by ultraviolet light.
- 10. The geogrid shall be CE Marked by an independent, authorised Certification Body to demonstrate that the product has been tested in accordance with the relevant European Standard relating to its specific use in construction, in accordance with the EU Construction Products Directive.
- 11. The product labelling must show the CE Mark, together with the Certification Body Number and the FPC (factory production control) number. 'Accompanying Documentation' indicating the relevant testing 'declared values', should be available on request.
- 12. Any geogrid offered for approval to the Engineer shall be accompanied by the relevant supporting documentation including details of the supplier, calculations demonstrating derivation of the appropriate long term safe design strength and the relevant and independently assessed partial factors of safety applied and product samples and specifications.

The information in this document is of an illustrative nature and is supplied without charge. It does not form part of any contract or intended contract with the user. Final determination of the suitability of any information or material for the use contemplated and the manner of use is the sole responsibility of the user and the user must assume all risk and liability in connection therewith.

Tensar is a registered trade mark

Geofabrics New Zealand Ltd

14 Goodman Place, P.O. BOX 12536, Penrose, Auckland, New Zealand Tel. (+64) 9 6346495 - Fax (+64) 9 6346492, FREEPHONE 0800 60 60 20 E-mail: sales@geofabrics.co.nz - Web site: www.geofabrics.co.nz Quality System AS/NZS ISO 9001:2008

The information contained in this brochure is general in nature. In particular the content of this brochure does not take account of specific conditions that may be present at your site. Site conditions may alter the performance and longevity of the product and in extreme cases may make the product wholly unsuitable. Actual dimensions and performance may vary. If your project requires accuracy to a certain specified tolerance level you must advise us before ordering the product from us. We can then advise whether the product will meet the required tolerances. Where provided, installation instructions cover installation of product to its instead contains the product are conducted as a to the installation instructions or their application to your site, please contact use and optimum performance. If you have any doubts as to the installation instructions or their application to your site, please contact use for clarification before commencing installation. This brochure should not be used for construction purposes and in all cases we recommend that advice be obtained from a suitably qualified consulting engineer or industry specialist before proceeding with installation. This brochure is current as at the date printed below. Geofabrics New Zealand Ltd may make amendments to this document at any time. Please refer to our website, or contact our nearest sales office to ensure you have the most currentson. @ Copyright held by Geofabrics New Zealand Ltd. All rights are reserved and no part of this publication may be copied without prior permission.