


Performance-related Product Specification Tensar TriAx[®] TX190L geogrid

General

1. The geogrid is manufactured in accordance with a management system which complies with the requirements of BS EN ISO 9001:2008.
2. The geogrid is manufactured from a punched polypropylene sheet, which is then oriented in three equilateral directions so that the resulting ribs of the triangular apertures have a high degree of molecular orientation which continues through the mass of the integral node.
3. The properties contributing to the performance of a mechanically stabilised layer are:



Geometrical	Longitudinal	Diagonal	Transverse	General
Rib pitch (mm)	60	60	-	
Mid-rib depth (mm)	-	1.9	1.6	
Mid-rib width (mm)	-	1.6	2.5	
Nodal thickness (mm)				5.4
Rib shape				rectangular
Aperture shape				triangular
Open area aspect ratio (%) ⁽¹⁰⁾				≥85
Mechanical				
Junction efficiency (%) ^(1,8)				90
Typical isotropic stiffness ratio ^(2,7)				0.60
Mean radial secant modulus at low strain (kN/m @ 0.5% strain) ^(2,9)				600±65
Durability				
Resistance of chemical degradation ⁽³⁾				96%
Resistance to weathering ⁽⁴⁾				98%
Resistance to oxidation				90%
Resistance to installation damage ⁽⁵⁾				>87%

Notes

1. Load transfer capability determined in accordance with GRI-GG2 and GRI-GG1 and expressed as a percentage of ultimate tensile strength.
2. Stiffness, (secant modulus), is determined in a test conducted in any in-plane direction and which records the maximum and minimum radial values when tested in accordance with ISO 10319:2008
3. Resistance to loss of ultimate load capacity when subjected to chemically aggressive environments in accordance with testing to EN12960 as part of a durability assessment in accordance with ISO13434:1999 7.3
4. Resistance to loss of ultimate load capacity when subjected to ultra-violet light and weathering in accordance with testing to EN12224 as part of a durability assessment in accordance with ISO13434:1999 7.2
5. Resistance to loss of radial stiffness when subjected to the effects of installation from a graded engineering fill. The procedure is in accordance with BS 8006:1995 and the radial stiffness is derived as in Note 3.
6. All geometrical and durability values are quoted as typical.
7. Declared as the ratio between the minimum and maximum value on a sample.
8. Declared at 95% confidence limit.
9. Declared at mean \pm standard deviation
10. Determination of the open area aspect ratio of a geogrid, Tensar International Ref QTC004, 2011

The information in this document supersedes any and all prior technical notes for the product designated above, is of an illustrative nature and supplied by Tensar International Limited free of charge for general information purposes only. Tensar reserves the right to amend product descriptions, properties and specifications at any time and without prior notice. This document does not form part of any contract or intended contract. Tensar International Limited excludes to the fullest extent lawfully permitted any and all liability whatsoever for any loss or damage howsoever arising out of the use of and reliance upon this information. It is your sole responsibility and you must assume all risk and liability for the final determination as to the suitability of any Tensar International Limited product and/or design for the use and in the manner contemplated by you in connection with a particular project.

Tensar, **Tensartech** and **TriAx** are registered trademarks

Tensar International Limited

Tel: **+44 (0) 1254 262431**
Fax: **+44 (0) 1254 266867**
E-mail: **sales@tensar.co.uk**
www.tensar-international.com

UK Head Office
Units 2 – 4 Cunningham Court
Shadsworth Business Park
Blackburn
Lancashire BB1 2QX
United Kingdom



Q 05288
ISO 9001:2008



EMS 86463
ISO 14001:2004

Copyright © Tensar International Limited 2012